

## LINO

SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE		100% POLIESTER / 95% POLIESTER, 5% BOMBAŽ 100% POLYESTER / 95% POLYESTER, 5% COTTON 100% POLIESTERSKO VLAKNO / 95% POLIESTERSKO VLAKNO, 5% PAMUK 100% POLYESTER / 95% POLYESTER, 5% BAUMWOLLE 100% POLIESTERE / 95% POLIESTERE, 5% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	142 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	440 gr/m2 +/-5%

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS7 TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1989 N (40,9%)	2545 N (74,9%)
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	181,89 N	211,55 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI 180 N	3 mm	3 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1+ DIN EN ISO 12947-2	50.000 OBRATOV/RUBS/OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	4 - 5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO
		4 - 5	4 - 5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB 82.02-2,3,4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631

Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si

TEST NEGORLJIVOSTI / TEST NEGORIVOSTI / FIRE RETARDANT / BRENNVERHALTEN / IGNIFUGO

Standard BS 5852 PART 1                      prestal / prošao / passed / überstanden / superato  
 Ignition source 0

ZAŠČITA TKANINE:  
 FABRIC PROTECTION:  
 ZAŠTITA TKANINE:  
 STOFFSCHUTZ:  
 PROTEZIONE TESSUTO:

VODOODBOJNI NANOS  
 WATER REPELLENT  
 VODOODBOJNI NANOS  
 WASSERABWEISEND  
 IDROPELENTE

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI                      COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE  
 MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE                      FARBNIANSEN SIND MOEGlich  
 DIFFERENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILE.



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631  
 Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si